



# Imron® AF740™ Polyurethane Clearcoat



## GENERAL

### DESCRIPTION

A 3.5 VOC compliant, high solids, polyurethane clearcoat designed to deliver high performance, excellent appearance, durability and application as part of the Imron AF700 Basecoat/Clearcoat system. It is formulated to provide balanced performance including smooth appearance, sag resistance and productive dry times.

### RECOMMENDED USES

Imron AF740 is recommended for use with Imron AF700 Basecoat in applications where either Skydrol resistance or the smoothest possible appearance (minimal orange peel) is required. Imron AF740 is ideal for accent stripes on business jets and single-engine aircraft. Imron AF740 is recommended for use as part of the Imron AF700 Basecoat/Clearcoat system.

The products referenced herein may not be sold in your market. Please consult your distributor for product availability.



## MIXING

### COMPONENTS

- Imron AF740 Polyurethane Clearcoat
- 13110S™ Activator
- 13100S™ Activator (repairs)
- 13930S™ Reducer
- 13765S™ Fast Reducer
- 13775S™ Medium Reducer

See Imron AF700 product data sheet for basecoat information.

### MIX RATIO

Thoroughly mix Imron AF740 prior to activation. Filter activated material prior to spray application.

<u>Components</u>	<u>Overall Parts by Volume</u>	<u>Small Parts/Repair Parts by Volume</u>
Imron AF740 Clearcoat	3	3
13110S / 13100S Activator	2 (13110S)	2 (13100S)
13930S / 13765S / 13775S Reducer	up to 1	up to 1

### VISCOSITY

10-13 seconds in a Zahn #3 cup. (Listed ranges were established using GARDCO EZ Zahn (AS™) Cups, measurements using other Zahn type cups may provide different results.)

### INDUCTION TIME

No induction time is required prior to application.

### POT LIFE

2 hours at 70°F (21°C) with 2 oz. of 13803S™ per RTS gallon.



**ADDITIVES**

**To improve pot life**

- Add up to 2 oz. 13801S™ per RTS gallon

**To improve dry time**

- Add up to 2 oz. 13803S per RTS gallon

**To improve striping/repair dry time**

- Add up to 1 oz. 13808S™ per RTS gallon

**Anti-Crater**

- Add up to 1 oz. 13813S™ per RTS gallon



---

**APPLICATION**

**SUBSTRATES AND SURFACE PREPARATION**

Surface preparation is critical to basecoat/clearcoat appearance. Follow basecoat or topcoat recoat-window guidelines to ensure proper adhesion. Substrate should always be thoroughly wiped and tacked immediately prior to clearcoat application.

**ENVIRONMENTAL CONDITIONS**

Subs and ambient temperature must be between 50°F (10°C) and 110°F (43°C). The substrate must be at least 5°F (3°C) above the dew point. Relative humidity should be below 90%. Heating activated paint above 110°F (43°C) may cause gelation. For optimum appearance spray Imron AF740 at 75°F (24°C) or warmer.

**GUN SETUP**

Imron AF740 can be applied with conventional, HVLP, airless, air-assisted airless, and electrostatic spray equipment using pressure or gravity fluid delivery.

**Conventional Fluid Tip**

Pressure Pot	1.0 mm-1.4 mm (.039”-.055”)
Gravity Feed	1.2 mm-1.6 mm (.047”-.063”)

**HVLP**

Pressure Pot	1.0 mm-1.4 mm (.039”-.055”)
Gravity Feed	1.2 mm-1.6 mm (.047”-.063”)

**FLUID DELIVERY**

Conventional	8-10 oz./minute
HVLP	8-10 oz./minute

**AIR PRESSURE**

Conventional	50-60 psi atomizing air
HVLP	25-30 psi atomizing air

**APPLICATION**

**Method 1:** Apply first coat medium wet with a 65% overlap. Allow to flash minimum 5 minutes followed by a second medium wet coat with a 65% overlap.

**Method 2:** Apply first coat as a cross-coat beginning from top to bottom then side to side. Allow to flash minimum of 5 minutes followed by a second coat in a side to side motion with a 65% overlap.

To achieve DFT goal of 2.0-2.5 mils, wet application should be between 4.0 – 5.0 mils wet.

**CLEANUP SOLVENTS**

- Axalta 107™ Low-VOC Gun & Equipment Cleaner
- Axalta 13920S™ Low-VOC Cleaner



**DRY TIMES**

**AIR DRY**

At 70°F (21°C) with 2 oz 13803S per ready-to-spray gallon  
 Dry to Touch 4 hours  
 Dry to Tape 8 hours

**FORCE DRY**

At 130°F (54°C)  
 Flash Before none required  
 Dry to Touch 2 hours  
 Dry to Tape 4 hours

**RECOAT**

Air Dry at 70°F (21°C) Scuff Sand required after 36 hours.  
 Force Dry at 130°F (54°C) Scuff Sand required after 12 hours

With 2 oz. 13803S or 13808S. Scuff Sand required after 12 hours.



**PHYSICAL PROPERTIES**

**VOC**

	<u>Less Exempts (LE)</u>	<u>As Packaged (AP)</u>
Imron AF740	3.8 lbs./gal	3.6 lbs./gal
Ready-to-Spray Imron AF740		
With 13110S and 13930S	3.3 lbs./gal	3.0 lbs./gal
With 13110S and 13895S	3.6 lbs./gal	3.5 lbs./gal

**FACTORY-PACKAGED CLEARCOAT**

Color Clear  
 Closed Cup Flash Point 20°F-73°F  
 Shelf Life 2 years (Unopened at 50°-110°F)

**READY-TO-SPRAY**

Theoretical Coverage 792 ft<sup>2</sup>/gal at 1 mil dry film thickness  
 Weight Solids 55%  
 Volume Solids 49%  
 Gallon Weight 8.5 lbs./gal.

**DRY FILM**

Gloss ≥90 measured at 60°  
 Recommended Film Thickness 1.8-2.5 mils

**COATING PERFORMANCE**

Chemical and Solvent Resistance Very Good  
 Weatherability Excellent  
 Humidity Resistance Excellent  
 Acid and Alkali Resistance Excellent  
 Abrasion Resistance Excellent  
 Flexibility Excellent

**VOC REGULATED AREAS**

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing usage and recommendations in the VOC Compliant Products Chart for your area.



---

## SAFETY AND HANDLING

For industrial use only by professional, trained painters. Not for sale to or use by the general public. Before using, read and follow all label and MSDS precautions. If mixed with other components, mixture will have hazards of all components.

Ready to use paint materials containing isocyanates can cause irritation of the respiratory organs and hypersensitive reactions. Asthma sufferers, those with allergies and anyone with a history of respiratory complaints must not be asked to work with products containing isocyanates.

Do not sand, flame cut, braze or weld dry coating without a NIOSH approved air purifying respirator with particulate filters or appropriate ventilation, and gloves.

Revised: January 2015

YOUR LOCAL WA STOCKIST



**PARK** T. 08 9444 9822  
UNIT 1/7 NEIL STREET, OSBORNE PARK, WA 6017

[WWW.PARKGROUP.COM.AU](http://WWW.PARKGROUP.COM.AU)

In the United States:  
**1.855.6.AXALTA**  
**axalta.us**

In Canada:  
**1.800.668.6945**  
**axalta.ca**

