

Standocryl VOC Xtreme Clear K9580



Standocryl VOC Xtreme Clear K9580 defines a new clearcoat era through the use of the latest innovative, patent-pending, Axalta Coating Systems binder technology, which uses the humidity in the drying process. Its energy-saving and super-fast drying properties distinguish this clearcoat from the rest. The application can be performed in one visit application and the clearcoat delivers outstanding gloss and flow. Maximum efficiency coupled with optimum topcoat appearance.

- Spectacular topcoat holdout.
- Extremely short drying times at low oven temperatures (15 mins at 40 °C).
- Dries extremely quickly at ambient temperatures (45 - 60 min at 20°C).
- Excellent for application in a single spray process (One Visit Application).
- Energy-saving thanks to extremely short drying times.
- Special Standox Xtreme Hardeners available for oven or ambient air drying.
- VOC compliant.

Super fast.




The Art of Refinishing.

Standocryl VOC Xtreme Clear K9580


Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Activated Standoblue Basecoat: Surfaces must be dried /flashed-off in accordance with TDS before application
Existing finishes: Surfaces must be sanded and degreased before application



| Clear | | Hardener | |
|--------|--------|---|--------|
| Volume | Weight | Volume | Weight |
| 2 | 100 | 1 | 50 |
| K9580 | | Xtreme Hardener Fast* Xtreme Hardener** Xtreme Hardener Slow*** | |



*Basecoat must be activated, change to a slower setting, if there is a risk of defects - when weather is humid.
**Basecoat must be activated, change to a slower setting, if there is a risk of defects - when weather is humid, change to a faster setting, if drying is too slow - when weather is dry.
***Basecoat must be activated, change to a faster setting, if drying is too slow - when weather is dry.

Pot life at 20°C: 1 hr



| | Spray nozzle | Spray pressure | |
|-----------|--------------|----------------|----------------------|
| Compliant | 1.2 - 1.3 mm | 1.8 - 2 bar | inlet pressure |
| HVLP | 1.2 - 1.3 mm | 0.7 bar | atomisation pressure |

see manufacturer's instructions



0.5 + 1

1 operation coat
1st: thin and closed
2nd: normal

final flash-off: 5 min - 10 min



For drying options, see details page.

VOC compliant

2004/42/IB(d)(420) 420: The EU limit value for this product (product category: IIB(d)) in ready to use form is maximum 420 g/l of VOC. The VOC content of this product in ready to use form is maximum 420 g/l.


Standocryl VOC Xtreme Clear K9580

Products


Standocryl VOC Xtreme Clear K9580

STANDOX XTREME HARDENER
 STANDOX XTREME HARDENER FAST
 STANDOX XTREME HARDENER SLOW

Product mix



Mixing ratios with special agents are available in the productmix table on Standowin IQ and in the specific TDS.



DIN 4: 13 - 15 s at 20°C




45 - 55 µm



| | Outside temperature | | |
|---|--------------------------------|--------------------------------|--------------------------------|
| | < 20°C | 20 - 30°C | > 30°C |
| Air dry (not below 10°C) 40-60 min / 20°C | Stadox Xtreme Hardener fast | Stadox Xtreme Hardener | Stadox Xtreme Hardener slow |
| Bake 10-15 min / 40-45°C | Stadox Xtreme Hardener | Stadox Xtreme Hardener | Stadox Xtreme Hardener slow |
| Optional: Bake 5-10 min / 60-65°C | Stadox Xtreme Hardener | Stadox Xtreme Hardener slow | |

Change to a slower setting, if there is a risk of defects - when the weather is humid.
 Change to a faster setting, if drying is too slow - when weather is dry.



Standocryl VOC Xtreme Clear K9580 can be recoated within 24 hours, without intermediate sanding



Clean after use with a suitable solventbased guncleaner.

Standocryl VOC Xtreme Clear K9580

Remarks

- Material has to be at room temperature (18-25°C) before use.
 - Allow additional time for preheating up to panel temperature.
 - Surplus ready for use material should not be returned to original can.
 - Humidity has an accelerating influence on the drying performance and potlife.
 - Once a can of clear or hardener has been opened, only 1 month remaining shelf life can be guaranteed.
 - Close can of clear and hardener tightly immediately after use, as both products will react with humid air and water and lose their hardening effect.
 - Application only with Standox Xtreme Hardeners.
 - Standoblue Basecoat has to be activated with 5% Standoblue Hardener directly before applying.
 - Standoblue Color Blend needs to be activated with 5% Standoblue Hardener directly before applying.
 - Do not use Standocryl VOC Xtreme Clear K9580 with Standox Plasticiser or Standox Special Matt or Standox Clearcoat Additives.
- Polishing: Prepare with finest available abrasive paper.
In countries without VOC legislation Hardened Standox Basecoat can be used as well.
15% Standox Hardener HS + 40% Standox MSB Thinner.
10% Standox Hardener VOC + 45% Standox MSB Thinner.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Standox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Standox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

