


Standox VOC Nonstop Primer Surfacer U7580

Good adhesion and corrosion properties characterise the Standox VOC Nonstop Primer Surfacer U7580. It builds on the success of the proven and well-known VOC Nonstop Primer Filler U7550 and can be applied directly to small bare steel or aluminium substrates when refinishing passenger cars. In combination with the new Standox VOC Plastic Additive U7590, it can be used to refinish most commonly used plastic substrates on passenger cars. With a single product it is possible to prime and coat several different types of substrate economically using the wet-on-wet application process.

- VOC compliant.
- Applied direct to small bare metal areas or to plastic.
- Good corrosion protection and adhesion properties.
- Very good application properties.
- Wet-on-wet application possible in a single spray process (One Visit Application).
- Short flash-off time.
- Long pot life.
- Can be overcoated with all Standox Basecoats.




The Art of Refinishing.

Stadox VOC Nonstop Primer Surfacer U7580

Product preparation - application STANDARD WET-ON-WET VOC



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned
Galvanised steel or aluminium, sanded and cleaned
Old or original paintwork well sanded and cleaned
OEM Primer (e-coat), finely sanded or unsanded and thoroughly cleaned. Remark: due to the wide variety of electrocoats present on the market, its quality can differ a lot. For this reason preferably scuff sand the e-coat
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned
Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



Filler		Activator		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
5	100	1	13	30 %	18
U7580		VOC 10-20		VOC T 15-30	
		VOC 20-25		VOC T 30-40	
		VOC 25-30			
		VOC 30-40			



Pot life at 20°C: 45 min - 1 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.5 - 2 bar	inlet pressure
HVLP	1.3 - 1.4 mm	0.7 bar	atomisation pressure
see manufacturer's instructions			



1 - 2 coats

final flash-off: 15 min - 8 hr



Basecoat + Clearcoat
Standocryl 2K Topcoats

VOC compliant


2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

Stadox VOC Nonstop Primer Surfacer U7580

Product preparation - application STANDARD WET-ON-WET HS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned
Galvanised steel or aluminium, sanded and cleaned
Old or original paintwork well sanded and cleaned
OEM Primer (e-coat), finely sanded or unsanded and thoroughly cleaned. Remark: due to the wide variety of electrocoats present on the market, its quality can differ a lot. For this reason preferably scuff sand the e-coat
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned
Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



Filler		Activator		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
3	100	1	20	20 - 23 %	14 - 16
U7580		HS 5-15 HS 15-25 HS 20-30 HS 25-40		VOC T 15-30 VOC T 30-40	



Pot life at 20°C: 45 min - 1 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.5 - 2 bar	inlet pressure
HVLP	1.3 - 1.4 mm	0.7 bar	atomisation pressure
see manufacturer's instructions			



1 - 2 coats

final flash-off: 15 min - 8 hr



Basecoat + Clearcoat
Standocryl 2K Topcoats

VOC compliant


2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

Stadox VOC Nonstop Primer Surfacer U7580

Product preparation - application STANDARD SANDING VOC



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned
 Galvanised steel or aluminium, sanded and cleaned
 Old or original paintwork well sanded and cleaned
 OEM Primer (e-coat), finely sanded or unsanded and thoroughly cleaned. Remark: due to the wide variety of electrocoats present on the market, its quality can differ a lot. For this reason preferably scuff sand the e-coat
 Surfaces pretreated with 2K polyester products and then finely sanded and cleaned
 Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



Filler		Activator		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
5	100	1	13	20 %	12
U7580		VOC 10-20 VOC 20-25 VOC 25-30 VOC 30-40		VOC T 15-30 VOC T 30-40	



Pot life at 20°C: 45 min - 1 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.4 - 1.8 mm	1.5 - 2 bar	inlet pressure
HVLP	1.4 - 1.8 mm	0.7 bar	atomisation pressure
see manufacturer's instructions			



2 - 3 coats intermediate and final flash-off: 5 min - 10 min



	VOC10-20/VOC20-25/VOC25-30/VOC30-40
20 °C	12 hr - 16 hr
60 - 65 °C	25 min - 30 min



Guideline for short wave IR equipment
 Half power: 2 min
 Full power: 8 min



P400 - P600



Basecoat + Clearcoat
 Standocryl 2K Topcoats

VOC compliant


2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

Stadox VOC Nonstop Primer Surfacer U7580

Product preparation - application STANDARD SANDING HS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned
Galvanised steel or aluminium, sanded and cleaned
Old or original paintwork well sanded and cleaned
OEM Primer (e-coat), finely sanded or unsanded and thoroughly cleaned. Remark: due to the wide variety of electrocoats present on the market, its quality can differ a lot. For this reason preferably scuff sand the e-coat
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned
Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



Filler		Activator		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
3	100	1	20	10 - 15 %	7 - 10
U7580		HS 5-15 HS 15-25 HS 20-30 HS 25-40		VOC T 15-30 VOC T 30-40	



Pot life at 20°C: 45 min - 1 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.4 - 1.8 mm	1.5 - 2 bar	inlet pressure
HVLP	1.4 - 1.8 mm	0.7 bar	atomisation pressure
see manufacturer's instructions			



2 - 3 coats intermediate and final flash-off: 5 min - 10 min



	HS5-15/HS15-25/HS20-30/HS25-40
20 °C	12 hr - 16 hr
60 - 65 °C	25 min - 30 min



Guideline for short wave IR equipment
Half power: 2 min
Full power: 8 min



P400 - P600



Basecoat + Clearcoat
Standocryl 2K Topcoats

VOC compliant


2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

Stadox VOC Nonstop Primer Surfacer U7580

Product preparation - application STANDARD PLASTICS VOC



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



New exterior common plastic car parts, tempering 60 min. 60-65°C / first cleaning use a pad ultrafine soaked in plastic cleaner / final cleaning use a cloth moistened with plastic cleaner.
Repairs to exterior common plastic car parts, sanded and cleaned.



Filler		Activator		Thinner			
Volume	Weight	Volume	Weight	Volume	Weight	Volume	Weight
5	100	1	13	40 %	26	0 - 10 %	0 - 6
U7580		VOC 10-20 VOC 20-25 VOC 25-30 VOC 30-40		U7590		VOC T 15-30 * VOC T 30-40 *	

* If needed add 0-10% Stadox Thinner VOC T 15-30 or VOC T 30-40



Pot life at 20°C: 45 min - 1 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.5 - 2 bar	inlet pressure
HVLP	1.3 - 1.4 mm	0.7 bar	atomisation pressure

see manufacturer's instructions



1 - 2 coats

final flash-off: 15 min - 8 hr



Basecoat + Elastified Clearcoat
Elastified 2K Topcoat

VOC compliant


This product mix is out of scope for VOC directive

Stadox VOC Nonstop Primer Surfacer U7580

Product preparation - application STANDARD PLASTICS HS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



New exterior common plastic car parts, tempering 60 min. 60-65°C / first cleaning use a pad ultrafine soaked in plastic cleaner / final cleaning use a cloth moistened with plastic cleaner.
Repairs to exterior common plastic car parts, sanded and cleaned.



Filler		Activator		Thinner			
Volume	Weight	Volume	Weight	Volume	Weight	Volume	Weight
3	100	1	20	30 %	22	0 - 10 %	0 - 7
U7580		HS 5-15 HS 15-25 HS 20-30 HS 25-40		U7590		VOC T 15-30 * VOC T 30-40 *	

* If needed add 0-10% Stadox Thinner VOC T 15-30 or VOC T 30-40




Pot life at 20°C: 45 min - 1 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.5 - 2 bar	inlet pressure
HVLP	1.3 - 1.4 mm	0.7 bar	atomisation pressure

see manufacturer's instructions



1 - 2 coats

final flash-off: 15 min - 8 hr



Basecoat + Elastified Clearcoat
Elastified 2K Topcoat

VOC compliant

This product mix is out of scope for VOC directive

Stadox VOC Nonstop Primer Surfacer U7580

Products


Stadox VOC Nonstop Primer Surfacer U7580

Stadox Hardener HS 15-25
Stadox Hardener HS 20-30
Stadox Hardener HS 25-40
Stadox Hardener HS 5-15
Stadox Hardener VOC 10-20
Stadox Hardener VOC 20-25
Stadox Hardener VOC 25-30
Stadox Hardener VOC 30-40

Stadox Thinner VOC 15-30
Stadox Thinner VOC 30-40
Stadox VOC Plastic Additive U7590


Stadox VOC Nonstop Primer Surfacer U7580

Product mix



Mixing ratios with special agents are available in the productmix table on Standwin IQ and in the specific TDS. The choice of Activator and Thinner should be made according to application temperature and size of repair.

HS 5-15	Accelerated fast hardener suitable for Micro and Spot repairs. Recommended for cooler application conditions. Suitable for Stadox Fillers for air drying at lower temperatures.
HS 15-25	Medium hardener suitable for panel and multi panel repairs. Recommended for application temperature of 15-25°C.
HS 20-30	Medium-slow hardener suitable for medium to large size repairs. Recommended also for warm conditions e.g. 20-30°C.
HS 25-40	Non-accelerated slow hardener suitable for medium to large size repairs. Recommended for use in hot climates e.g. 25-40°C.
VOC 10-20	Accelerated fast hardener suitable for Micro Repair, spot and panel repairs. Recommended for cooler application conditions e.g. 10-20°C.
VOC 20-25	Medium hardener suitable for panel and multi panel repairs. Recommended for application temperature of 20-25°C.
VOC 25-30	Medium-slow hardener suitable for medium to large size repairs. Recommended also for warm conditions e.g. 25-30°C.
VOC 30-40	Non-accelerated slow hardener suitable for medium to large size repairs. Recommended for use in hot climates e.g. 30-40°C.
VOC T 15-30	Medium thinner suitable for panel, multi panel and large size repairs. Recommended for application temperature e.g. 15-30°C.
VOC T 30-40	Slow thinner for medium to large size repairs. Recommended for use in hot climates e.g. 30-40°C.



ISO 4: 37 - 68 s at 20°C
DIN 4: 16 - 24 s at 20°C



30 - 50 µm non-sanding
60 - 120 µm sanding



Clean after use with a suitable solventbased guncleaner.

Stadox VOC Nonstop Primer Surfacer U7580

Remarks

- Material has to be at room temperature (18-25°C) before use.
 - Allow additional time for preheating up to panel temperature.
 - On bare steel, galvanized steel and soft aluminium, Acid Primer or epoxy primer can be applied but is not mandatory.
 - When using Acid Primer no IR drying is allowed.
 - Non-sanding plastic primer-surfacer setting can also be used on adjacent non plastic panels.
 - For air drying we recommend a minimum temperature of +15°C.
 - Sanding version is limited to DFT max 100µm when used over Acid Primer.
 - Surplus ready for use material should not be returned to original can.
 - In order to achieve elastic properties the use of Stadox Plasticiser is not required.
 - Bare metal sand-through areas which needs to be overcoated with Stadox Polyester Spray Filler U1100 or Stadox Polyester Stopper, the fastest overcoatability can be achieved with Stadox HS Hardener 5-15 in mixing ratio 3:1 + 20-25% Stadox VOC Thinner. The flash off time before recoating with polyester products must be a minimum of 30-40 minutes at 20°C.
 - Stadox VOC Nonstop Primer Surfacer U7580 Black and Light Grey can be mixed with each other to achieve various grey shades if desired.
 - Stadox 2K Thinners can be used as alternatives for Stadox VOC Thinners in the same mixing ratios.
 - In countries without VOC legislation Stadox Basecoat can be used as well.

 - In countries without VOC legislation the amount of thinner can be increased by 5% when preparing the product mix for wet-on-wet application on metal parts.
-

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Stadox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Stadox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

